

QUALITEK®

DELTA® 350 Solder Paste Rosin Activated (RA)

DESCRIPTION

350 is a non-corrosive, non-conductive fully activated rosin solder paste designed for surface mount applications.

BENEFITS

- Excellent Activity
- No slump
- Non-corrosive

APPLICATION

PRINTING / PARTICLE SIZE

≥ 50 mil pitch: Use -200 +325 mesh

≥ 16 mil pitch: Use -325 +500 mesh

≤ 16 mil pitch: Use -400 +635 mesh

ALLOYS

Sn63/Pb37, Sn62/Pb36/Ag2, Sn10/Pb88/Ag2, LF alloys etc.

(Meets J-STD-006 Specification)

METAL CONTENT

Stencil Printing: 90%

Screen Printing: 88%

REFLOW PROFILE

The melting temperature of the solder and the heat resistance of components determine reflow Profile. 350 can be processed in most reflow media, (i.e. IR, Vapor-phase, Forced convection, etc.). Ramp rate of 2.5-3.0°C per second is desirable, since most components are rated for 4.0°C per second.

PHYSICAL / CHEMICAL CHARACTERISTICS

Color and Appearance	Metallic Gray
Copper Mirror Test	Pass
Surface Insulation Resistance-Ohms	
J-STD-004	1.0 x 10 ¹⁰
pH-5% Aqueous Solution (Flux Extract)	4.0 – 4.6
Softening Point	80°C
Viscosity	
Malcom ¹	175 - 205 kcps, 90% metal, (-325+500 mesh)
Brookfield ²	1,000 kcps +/- 10%, 90% metal, (-325+500 mesh)
Tack	
Time	4 - 8 Hours

SHIPPING & STORAGE

Recommended Storage Temperature 35°-50°F

SHELF LIFE

Unopened Container	35°-65°F	6 Months (from DOM)
	77°F	1 Month (from DOS)

1. Malcom PCU-Series, 10 RPM, 25°C
2. Brookfield RVTD, TF spindle, 5 RPM, 25°C, 0.75" spindle depth

Delta® is a registered trademark of Qualitek International, Inc.

TEL: +44 (0) 151 334 0888 FAX: +44 (0) 151 346 1408 E-mail: sales@qualitek-europe.com Internet: www.qualitek.com
9 Apex Court, Bassendale Road, Wirral International Business Park, Bromborough, Wirral, CH62 3RE


QUALITEK

WORLDWIDE BRANCHES: UNITED KINGDOM – MEXICO – CHINA – PHILIPPINES – SINGAPORE-USA

This data is based on information that the manufacturer believed to be reliable and offered in good faith. Qualitek International, Inc. makes no warranties expressed or implied as to its accuracy and assumes no responsibilities and liabilities arising out of its use by others as conditions and methods of use of the products is beyond the control of Qualitek International, Inc. The user must determine the suitability of the product before using it on a commercial basis. The warranties extend only to the conformity of the product to the physical descriptions. In no event will Qualitek International, Inc. be responsible for special, incidental and consequential damages whether the claim is in contract, negligence or otherwise.

Rev. 082099-350

Consult MSDS for health and safety information



Sn10/Pb88/Ag2